

ACRYLITE® LED 8N LD48

Polymethyl Methacrylate Acrylic

Evonik Cyro LLC

Message:

ACRYLITE® LED 8N LD48 Acrylic Molding Compound is a highly transparent light guide material based on ACRYLITE® 8N. In addition to the typical properties of ACRYLITE®, such as

- Excellent weather resistance
- UV-stability
- Good flow, high mechanical strength

ACRYLITE® LED 8N LD48 is developed for edge lit LED applications. The light scattering properties convert the light guide to a full illuminated panel. Furthermore, the material allows for a completely transparent view through the light guide when it is not illuminated. This opens a new degree of freedom for designers. ACRYLITE® 8N LD12 is recommended for panels with a distance of 24 cm to 48 cm (9.45 in to 18.9 in) between two light injecting LED strips.

Application:
Injection molding or extrusion.

General Information	
Features	Good Flow Good UV Resistance Good Weather Resistance High Clarity High Strength
Uses	Lighting Applications Lighting Diffusers
Agency Ratings	EC 1907/2006 (REACH)
Appearance	Clear/Transparent
Forms	Pellets
Processing Method	Extrusion Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Apparent Density	0.66	g/cm ³	ASTM D1895
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	3.3	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.70	%	ASTM D955
Water Absorption (Equilibrium)	< 0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	95		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3240	MPa	ASTM D638
Tensile Strength	77.9	MPa	ASTM D638

Tensile Elongation			ASTM D638
Yield	4.0 to 6.0	%	
Break	4.0 to 6.0	%	
Flexural Modulus	3450	MPa	ASTM D790
Flexural Strength	112	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.35 mm)	19	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Annealed, 6.35 mm)	100	°C	ASTM D648
Vicat Softening Temperature	108	°C	ASTM D1525
CLTE - Flow (0 to 100°C)	7.2E-5	cm/cm/°C	ASTM D696
Optical	Nominal Value	Unit	Test Method
Transmittance (3200 µm)	92.0	%	ASTM D1003
Haze (3200 µm)	< 2.0	%	ASTM D1003
Yellowness Index (3.20 mm)	< 1.0	YI	ASTM D1925

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT