

Stanyl® TE373

Polyamide 46
DSM Engineering Plastics

Message:

Stanyl® TE373 is a Polyamide 46 (Nylon 46) material. It is available in Asia Pacific, Europe, or North America.
Important attributes of Stanyl® TE373 are:
Heat Stabilizer
Wear Resistant

General Information				
Additive		Heat Stabilizer		
Features		Good Wear Resistance		
		Heat Stabilized		
Multi-Point Data		Shear Modulus vs. Temperature (ISO 11403-1)		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.17	--	g/cm³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	2.0	--	%	
Flow	2.0	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	3.4	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	2800	1000	MPa	ISO 527-2
Tensile Stress (Yield)	85.0	50.0	MPa	ISO 527-2
Nominal Tensile Strain at Break	10	15	%	ISO 527-2
Flexural Modulus	2400	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	4.0	4.0	kJ/m²	
23°C	5.0	10	kJ/m²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	110	120	kJ/m²	
23°C	150 kJ/m²	No Break		
Notched Izod Impact Strength				ISO 180/1A
-40°C	4.0	4.0	kJ/m²	
23°C	5.0	9.0	kJ/m²	
Thermal	Dry	Conditioned	Unit	Test Method

Heat Deflection Temperature (1.8 MPa, Unannealed)	190	--	°C	ISO 75-2/A
Melting Temperature ¹	295	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	8.5E-5	--	cm/cm/°C	
Transverse	1.1E-4	--	cm/cm/°C	
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0 to 8.0		hr	
Rear Temperature	280 to 320		°C	
Middle Temperature	300 to 320		°C	
Front Temperature	300 to 320		°C	
Nozzle Temperature	300 to 320		°C	
Processing (Melt) Temp	310 to 320		°C	
Mold Temperature	80.0 to 120		°C	
Injection Rate	Moderate-Fast			
Back Pressure	2.00 to 10.0		MPa	
Screw Compression Ratio	2.5:1.0			
NOTE				

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

