Jam PE 12X01

Linear Low Density Polyethylene

Jam Petrochemical Company

Message:

Jam PE 12X01 is a Linear Low Density Polyethylene product. It is available in Africa & Middle East. Typical application: Film. Primary characteristic: butene comonomer.

General Information			
Features	Butene Comonomer		
	Terpolymer		
Uses	Film		
Physical	Nominal Value	Unit	Test Method
	0.912 to 0.916	g/cm ³	ASTM D1505
Density	0.912 (0 0.916	g/cm	ASTM DT505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.95	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	μm	
Tensile Strength		b	ASTM D882
MD : Yield,25 µm, Blown Film	10.8	MPa	
TD : Yield,25 µm, Blown Film	10.8	MPa	
MD : Break, 25 µm,Blown Film	30.5	MPa	
TD : Break, 25 µm,Blown Film	37.5	МРа	
Tensile Elongation			ASTM D882
MD : Break, 25 µm,Blown Film	770	%	
TD : Break, 25 µm,Blown Film	680	%	
Dart Drop Impact (25 µm, Blown Film)	120	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 25 µm, Blown Film	400	g	
TD : 25 μm, Blown Film	180	g	
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 25.0 µm, Blown Film)	20		ASTM D1790
Haze (25.0 µm, Blown Film)	40	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

