Tarflen® ST

Polytetrafluoroethylene

Grupa Azoty S.A.

Message:

Tarflen®ST is a polytetrafluoroethylene (PTFE) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

Tarflen®The main features of ST are:

Flame Retardant

good weather resistance

chemical resistance

Wear-resistant

Typical application areas include:

engineering/industrial accessories

application of coating

Wire and cable

Sealing applications

Hose

General Information								
Features	Low friction coefficient Moisture proof Good liquidity Good chemical resistance							
					Good wear resistance			
					Good weather resistance			
	Flame retardancy							
	Uses	Bar						
Cable sheath								
Washer								
Valve/valve components								
Pipe								
Piping system								
Seals								
Accessories								
Coating application								
Profile								
Fabric coating								
Forms	Particle							
Physical	Nominal Value	Unit	Test Method					
Density	2.15	g/cm³	ISO 1183					
Mechanical	Nominal Value	Unit	Test Method					
Tensile Stress (Yield)	20.0	MPa	ISO 527-2					

Tensile Strain (Break)	260	%	ISO 527-2	
Thermal	Nominal Value	Unit	Test Method	
Linear thermal expansion coefficient			ISO 11359-2	
Flow: 23 to 100°C	1.8E-4	cm/cm/°C	ISO 11359-2	
Lateral: 23 to 100°C	1.3E-4	cm/cm/°C	ISO 11359-2	
Additional Information				
Bulk Density, No Standard: 0.6 kg/dm ³				
Extrusion instructions				

Molding Pressure: 35 to 40 MpaMolding Temperature: 370 °C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

