# Beetafin® L9047

### Polyurethane (Polyester based)

#### BIP (Oldbury) Limited

#### Message:

An anionic, soft, highly flexible, light fast polyester based, aliphatic aqueous polyurethane dispersion. Thickened for ease of application.

Characteristics:

Abrasion resistance

Gives soft, highly extensible, tough films with a dry feel

Gives high clarity films that do not discolour on exposure to daylight

- Normal high gloss finish may be modified by the addition of a recommended duller

Good adhesive properties on synthetic and natural materials

Applications:

Leather Adhesive

Plastic Coatings & Adhesive

Textile Adhesive

Viscosity (25°C)

**Heat-Seal Adhesives** 

General Information							
Features	Aliphatic						
	Good Abrasion Resistance Good Adhesion Good Flexibility Good Toughness						
					High Clarity		
					Soft		
Uses	Adhesives						
	Coating Applications						
	Printing Ink						
	<b>Textile Applications</b>						
Physical	Nominal Value	Unit					
рН	8.0						
Solids Content	40	%					
Films	Nominal Value	Unit					
Tensile Modulus - 100%	3.50	МРа					
Tensile Strength - MD (Break)	30.0	MPa					
Tensile Elongation - MD (Break)	1000	%					
Uncured Properties	Nominal Value	Unit	Test Method				

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

5.0

Pa·s

Brookfield

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

