Karina IVORY PVC COMPOUND 651D35/1-D-IS

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

FUNGI RESISTANT PVC COMPOUND RECOMMENDED FOR INJECTION OF BATHROOM CARPET.

General Information			
Features	Fungus Resistant		
Appearance	lvory		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.30 to 1.36	g/cm³	ASTM D792
Cadmium Content	< 50	ppm	IEC 62321
Chromium Content	< 100	ppm	IEC 62321
Color	0.00OK		ME 12
Color a	-2.04 to 0.960		ME 12
Color b	0.480 to 3.48		ME 12
Color L	87.4 to 90.4		ME 12
Mercury Content	< 100	ppm	IEC 62321
Bromine Content	< 100	ppm	IEC 62321
Lead Content	< 100	ppm	IEC 62321
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	63 to 67		NBR 7456
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 5.88	MPa	ASTM D638
Tensile Elongation (Yield)	> 250	%	ASTM D638
NOTE			
1.	24 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

