

Sinpolene TPP1010

Polypropylene Homopolymer

Teknor Apex Asia Pacific PTE. LTD.

Message:

Sinpolene TPP1010 is a Polypropylene Homopolymer (PP Homopolymer) material filled with 10% talc. It is available in Asia Pacific for injection molding.

General Information			
UL YellowCard	E142591-223228		
Filler / Reinforcement	Talc,10% Filler by Weight		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.950	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.0 to 1.4	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	30.0	MPa	ASTM D638
Tensile Elongation (Break)	20	%	ASTM D638
Flexural Modulus	2000	MPa	ASTM D790
Flexural Strength	50.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	25	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	126	°C	ASTM D648
Vicat Softening Temperature	153	°C	ASTM D1525 ¹
NOTE			

1. Loading 1 (10 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT