

Mirathane™ S895

Thermoplastic Polyurethane Elastomer (Polyether)

Miracll Chemicals Co., Ltd.

Message:

Mirathane™ S895 is a Thermoplastic Polyurethane Elastomer (Polyether) (TPU-Polyether) product. It is available in Asia Pacific.

Characteristics include:

Chemical Resistant

Wear Resistant

General Information			
Features	Good Abrasion Resistance		
	Low Compression Set		
	Oil Resistant		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	94		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Abrasion Loss	30.0	mm ³	DIN 53516
Service Temperature	-40 to 110	°C	
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	8.00	MPa	
300% Strain	18.0	MPa	
Tensile Strength (Yield)	25.0	MPa	ASTM D412
Tensile Elongation (Break)	420	%	ASTM D412
Tear Strength	80.0	kN/m	ASTM D624
Compression Set			ASTM D395
70°C, 22 hr	25	%	
100°C, 24 hr	32	%	
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature ¹	-50.0	°C	DSC
Extrusion	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	3.0 to 4.0	hr	
Cylinder Zone 1 Temp.	200	°C	
Cylinder Zone 2 Temp.	190	°C	
Cylinder Zone 3 Temp.	185	°C	
Die Temperature	205	°C	
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

