

LUVOCOM® 1100-8326

Polyethersulfone
Lehmann & Voss & Co.

Message:

LUVOCOM® 1100-8326 is a polyethersulfone (PES) material, and the filler is carbon fiber reinforced material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

LUVOCOM®The main features of 1100-8326 are:

- anti-warping
- Good stiffness
- Wear-resistant
- Lubrication

Typical application areas include:

- engineering/industrial accessories
- Electrical/electronic applications
- Aerospace
- Sporting goods
- medical/health care

General Information			
Filler / Reinforcement	Carbon fiber reinforced material		
Additive	PTFE lubricant		
Features	Low friction coefficient		
	Low warpage		
	Rigid, good		
	Good strength		
	Good wear resistance		
	Lubrication		
Uses	Pump parts		
	Bushing		
	Gear		
	Electrical/Electronic Applications		
	Engineering accessories		
	Aerospace applications		
	Sporting goods		
	Medical/nursing supplies		
	Bearing		
Appearance	Natural color		
Physical	Nominal Value	Unit	Test Method
Density	1.53	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (345°C/5.0 kg)	4.00	cm ³ /10min	ISO 1133
Molding Shrinkage	0.20 - 0.40	%	DIN 16901

Water Absorption (23°C, 24 hr)	< 0.10	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10000	MPa	ISO 527-2
Tensile Stress (Break)	91.0	MPa	ISO 527-2
Tensile Strain (Yield)	1.7	%	ISO 527-2
Flexural Modulus	8000	MPa	ISO 178
Flexural Stress	137	MPa	ISO 178
Flexural Strain at Flexural Strength	2.2	%	ISO 178
Maximum operating temperature-Short Term	200	°C	
Insulation Resistance		ohms	IEC 60167
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	20	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	220	°C	ISO 75-2/A
Continuous Use Temperature	180	°C	UL 746B
CLTE - Flow	2.0E-5	cm/cm/°C	DIN 53752
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+5	ohms	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	150	°C	
Drying Time - Desiccant Dryer	3.0 - 5.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	355 - 375	°C	
Middle Temperature	360 - 380	°C	
Front Temperature	350 - 370	°C	
Nozzle Temperature	340 - 360	°C	
Processing (Melt) Temp	350	°C	
Mold Temperature	120 - 200	°C	
Injection instructions			

General

In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines.

Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.

Lengthy dwell times for the melts in the cylinder should be avoided.

Lower the temperatures during interruptions!

Predrying (optional)

It is advisable to predry the granulate with a suitable dryer immediately before processing.

The granulate may absorb moisture from the air.

Delivery Form & Storage

Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.

Preferably storage should be effected in dry and normally temperatured rooms

Additional Information

During processing the moisture level should not exceed 0.05%, otherwise porosity and surface defects (e.g. smearing) may occur. To avoid internal stresses, a low shear load should be used for processing. The parts may be tempered at a later stage to reduce internal stresses.

The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.

High-temperature polymers place increased demands on the tool steels employed.

Please contact us for further information.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

