

POLIGOM G/30 C

Ethylene Propylene Diene Terpolymer

Crosspolimeri S.p.A.

Message:

POLIGOM G/30 C is a crosslinkable EPR/EPDM.

POLIGOM G/30 C is a chemically crosslinkable rubber for low voltage cable insulation and sheathing.

It is a conveniently grafted compound able to react in presence of moisture and of a catalyst MAC/202 or MAC/308 PSL.

These two compounds, separately stored, must be mixed before starting extrusion in the ratio:

GRAFTING/CATALYST 95/5

Cerfity: HD221 S3 EI4-EI6, AS/NZS 3808:2000 X-90, R-E-110, E-110-R

General Information			
Features	Crosslinkable		
Uses	Low voltage insulation		
	Cable sheath		
	Wire and cable applications		
Agency Ratings	AS/NZS 3008:2000 X-90		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.930	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	1.0 - 5.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	82		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	> 10.0	MPa	IEC 60811
Tensile Strain (Break)	> 600	%	IEC 60811
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (150°C, 168 hr)	10	%	IEC 60811
Change in Tensile Strain at Break in Air (150°C, 168 hr)	-12	%	IEC 60811
Thermal	Nominal Value	Unit	Test Method
Thermoset ¹			IEC 60811
250°C	70	%	IEC 60811
Residual : 250°C	5.0	%	IEC 60811
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+14	ohms · cm	IEC 60167
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	160	°C	
Cylinder Zone 2 Temp.	175	°C	

Cylinder Zone 3 Temp.	190	°C
Cylinder Zone 4 Temp.	205	°C
Cylinder Zone 5 Temp.	210	°C
Die Temperature	215	°C

Extrusion instructions

CROSSLINKING:Crosslinking of the finished product is obtained by:
 Immersion of the bobbin into hot water at 85/90 °C for two hours (up to 3 mm thickness).
 Steam treatment at 0.15 for bar 5/6 hours.
 Faster ambient curing is possible depending from the atmospheric conditions.

NOTE

1. 20 N/cm²

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

