

PEARLCOAT® Activa D198K

Thermoplastic Polyurethane Elastomer

Lubrizol Advanced Materials, Inc.

Message:

PEARLCOAT® Activa D198K is an aliphatic based thermoplastic polyurethane of low hardness, supplied in the form of natural pellets. This product gives an inherent "low gloss aspect" on the final product surface after extrusion processing. Featuring low gel content as well as low temperature flexibility, it is ideally suited for extrusion or co-extrusion onto polar substrates.

General Information	
Features	Low speed solidification crystal point Flexibility at low temperatures Gloss, low Hardness, low aliphatic
Agency Ratings	EC 1907/2006 (REACH)
Appearance	Natural color
Forms	Particle
Processing Method	Co-extrusion molding Extrusion

Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.10	g/cm ³	ASTM D792
20°C	1.10	g/cm ³	ISO 2781
Moisture Content	1000	ppm	Internal method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	70		ASTM D2240, ISO 868
Mechanical	Nominal Value	Unit	Test Method
Abrasion Loss	30.0	mm ³	ISO 4649
Extruder Screw L/D Ratio	25:1		
Extruder Screw Compression Ratio	3:1		
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412, ISO 527
100% strain	5.80	MPa	ASTM D412, ISO 527
300% strain	13.0	MPa	ASTM D412, ISO 527
Tensile Strength (Yield)	25.0	MPa	ASTM D412, ISO 527
Tensile Elongation (Break)	460	%	ASTM D412, ISO 527
Tear Strength			
-- ¹	55.0	kN/m	ASTM D624
-- ²	55	kN/m	ISO 34-1

Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-33.0	°C	ISO 11357-2
Melting Temperature ³	135 - 145	°C	Internal method
Extrusion	Nominal Value	Unit	
Drying Temperature	90.0 - 100	°C	
Drying Time	1.0 - 2.0	hr	
Cylinder Zone 1 Temp.	185 - 205	°C	
Cylinder Zone 2 Temp.	190 - 210	°C	
Cylinder Zone 3 Temp.	195 - 215	°C	
Cylinder Zone 4 Temp.	190 - 210	°C	
Die Temperature	185 - 205	°C	
Extrusion instructions			
Cooling: AirSpeed: 60 rpmThickness Die: 0.2 mm			
NOTE			
1.	C mould		
2.	Method B, right-angle specimen (without cut)		
3.	Temperature at which MFI = 10 g/10 min @ 21.6 kg		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

