Siveras™ LX70M50

Liquid Crystal Polymer

Toray Resin Company

Message:

Siveras™ LX70M50 is a Liquid Crystal Polymer (LCP) product filled with 50% glass\mineral. It is available in Asia Pacific, Europe, or North America. Primary characteristic: flame rated.

| General Information | | | |
|---|------------------------------------|----------|-----------------|
| Filler / Reinforcement | Glass\Mineral,50% Filler by Weight | | |
| Features | Low Anisotropy | | |
| Part Marking Code | >LCP-(GF+MD)50< | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.80 | g/cm³ | ASTM D792 |
| Molding Shrinkage | | | Internal Method |
| Across Flow: 1.00 mm ¹ | 0.40 | % | |
| Flow: 1.00 mm ² | 0.15 | % | |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | 110 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 2.5 | % | ASTM D638 |
| Flexural Modulus | 15500 | MPa | ASTM D790 |
| Flexural Strength | 150 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | 60 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 240 | °C | ASTM D648 |
| CLTE - Flow | 1.6E-5 to 2.0E-5 | cm/cm/°C | ASTM D696 |
| Flammability | Nominal Value | | Test Method |
| Flame Rating (0.380 mm) | V-0 | | UL 94 |
| NOTE | | | |
| 1. | 80x80x1 | | |
| 2. | 80x80x1mm | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

