

AME™ 6001 INF

Vinyl Ester
Ashland Performance Materials

Message:

Infusion/RTM resins
Resin Properties
Greater than 5% tensile elongation
Outstanding fatigue failure resistance
Excellent surface profile
Excellent toughness

General Information		
Features	Fatigue Resistant	
	Good Surface Finish	
	Good Toughness	
Processing Method	Resin Transfer Molding	
Physical	Nominal Value	Unit
Solution Viscosity	125 to 165	mPa · s
Thermal	Nominal Value	Unit
Glass Transition Temperature	154 to 171	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT