

Envirez® SS 71419

Thermoset Polyester

Ashland Performance Materials

Message:

Cast polymers - Solid Surface Resins
Properties
Contains bio-derived material

General Information		
Features	Renewable Resource Content	
Processing Method	Casting	
Physical	Nominal Value	Unit
Solution Viscosity	550	mPa·s
Additional Information	Nominal Value	Unit
Gel to Peak	10.0	min
Peak Exotherm	193	°C
Uncured Properties	Nominal Value	Unit
Gel Time	20	min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT