

# LARIPUR® LPR 6325

Thermoplastic Polyurethane Elastomer (Polyester)

COIM S.p.A.

Message:

LARIPUR® LPR 6325 is a thermoplastic polyurethane elastomer (polyester)(TPU-polyester) material. This product is available in North America, Latin America or Europe. The processing method is injection molding.

LARIPUR®The main features of LPR 6325 are:

Good toughness

Good tear strength

good weather resistance

General Information			
Features	Low Temperature Flexibility		
	Good tear strength		
	Good weather resistance		
	Good toughness		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	62		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	350	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
50% strain	21.2	MPa	ASTM D412
100% strain	24.1	MPa	ASTM D412
300% strain	51.1	MPa	ASTM D412
Tensile Strength (Break)	70.2	MPa	ASTM D412
Tensile Elongation (Break)	370	%	ASTM D412
Tear Strength	193	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	156	°C	ASTM D1525
Additional Information			

Abrasion loss, DIN 53516: 40 mm<sup>3</sup>Tosion Test, ASTM D 1043, 20° C: 80 MPaTosion Test, ASTM D 1043, -20° C: 460 MPaImpact Test, ASTM D 256, -20° C: 4.7 KJ/m<sup>2</sup>

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

