

Lucky Enpla LGF2201F

Polycarbonate + ABS

Lucky Enpla Co LTD

Message:

Lucky Enpla LGF2201F is a polycarbonate + acrylonitrile butadiene styrene (PC + ABS) product, which contains a 20% glass fiber reinforced material. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region. Lucky Enpla LGF2201F applications include electrical/electronic applications and housing. The main characteristics are: halogen-free.

General Information			
UL YellowCard	E217401-100913628		
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Features	Halogen-free		
Uses	Electrical/Electronic Applications		
	Shell		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.32	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.10 - 0.30	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	90.2	MPa	ASTM D638
Flexural Modulus ²	5490	MPa	ASTM D790
Flexural Strength ³	137	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (3.18 mm)	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	112	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	70.0 - 90.0	°C	
Drying Time	2.0 - 3.0	hr	
Rear Temperature	230 - 250	°C	
Middle Temperature	240 - 260	°C	
Front Temperature	240 - 260	°C	
Nozzle Temperature	250 - 270	°C	
Mold Temperature	30.0 - 60.0	°C	
Back Pressure	0.490 - 1.47	MPa	
Screw Speed	40 - 70	rpm	
Injection instructions			
Resin Temperature: 250-270°CInjection Pressure (1st Pressure): 800-1200 kg/cm²Injection Pressure (2nd Pressure): 500-800 kg/cm²			
NOTE			

1.	10 mm/min
2.	5.0 mm/min
3.	5.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

