

Nylfor® B2 GB/30 NATURALE

Polyamide 6

SO.F.TER. SPA

Message:

Standard viscosity polyamide 6, 30% glass bead reinforced

General Information			
Filler / Reinforcement	Glass Bead,30% Filler by Weight		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm ³	ASTM D792
Molding Shrinkage	0.85	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	6.3	%	
Equilibrium, 23°C, 50% RH	1.9	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4600	MPa	ASTM D638
Tensile Strength (Break)	65.0	MPa	ASTM D638
Tensile Elongation (Break)	6.0	%	ASTM D638
Flexural Modulus	4000	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact (23°C)	40	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	90.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	425	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	4.0	hr	
Rear Temperature	240	°C	
Middle Temperature	260	°C	
Front Temperature	270	°C	

Mold Temperature	60.0 to 80.0	°C
------------------	--------------	----

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

