

KOPA® KN333HSBL

Polyamide 66
Kolon Plastics, Inc.

Message:

KOPA® KN333HSBL is a Polyamide 66 (Nylon 66) product. It is available in Asia Pacific, Europe, Latin America, or North America.
Characteristics include:
Flame Rated
Heat Resistant

General Information			
Features	High Heat Resistance		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.1 to 1.3	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60% RH)	1.3	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	82.4	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	50	%	ASTM D638
Flexural Modulus (23°C)	2840	MPa	ASTM D790
Flexural Strength (23°C)	118	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648A
0.45 MPa, Unannealed	225	°C	
1.8 MPa, Unannealed	70.0	°C	
Peak Melting Temperature	255	°C	ASTM D3418
CLTE - Flow	7.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	20	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.30		ASTM D150
Arc Resistance	128	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-2		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT