

Celstran® PA66-GF50-02 P7

Polyamide 66

Celanese Corporation

Message:

Material code according to ISO 1043-1: PA66

Heat stabilized Nylon 66 reinforced by 50 weight percent long glass fibers. The pellets are cylindrical and normally as well as the embedded fibers 7 mm long.

Parts molded of CELSTRAN have outstanding mechanical properties such as high strength and stiffness combined with high heat deflection.

The notched impact strength is increased at elevated and low temperatures due to the fiber skeleton built in the parts. The long fiber reinforcement reduces creep significantly.

The very isotropic shrinkage in the molded parts minimizes the warpage.

Complex parts can be manufactured with high reproducibility by injection molding.

Can be used for substituting die cast metal with the advantage of Weight reduction, no corrosion problems, no post treatment.

General Information			
Filler / Reinforcement	Long glass fiber, 50% filler by weight		
Additive	heat stabilizer		
Features	Low warpage		
	Rigidity, high		
	High strength		
	Impact resistance, good		
	Good creep resistance		
	Low temperature impact resistance		
	Thermal Stability		
Uses	Metal substitution		
RoHS Compliance	Contact manufacturer		
Forms	Particle		
Processing Method	Injection molding		
Resin ID (ISO 1043)	PA66		
Physical	Nominal Value	Unit	Test Method
Density	1.57	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	16600	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	260	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	2.1	%	ISO 527-2/1A/5
Thermal	Nominal Value	Unit	Test Method
Melting Temperature ¹	260	°C	ISO 11357-3
Injection	Nominal Value	Unit	

Drying Temperature	70.0 - 80.0	°C
Drying Time	2.0 - 4.0	hr
Suggested Max Moisture	0.15	%
Hopper Temperature	70.0 - 80.0	°C
Rear Temperature	280 - 285	°C
Middle Temperature	280 - 290	°C
Front Temperature	290 - 300	°C
Nozzle Temperature	310 - 320	°C
Processing (Melt) Temp	310 - 320	°C
Mold Temperature	90.0 - 120	°C
Injection Pressure	120 - 150	MPa
Injection Rate	Moderate	
Holding Pressure	50.0 - 80.0	MPa
Back Pressure	0.00 - 3.00	MPa

Injection instructions

Manifold Temperature: 300 to 315°C Zone 4 Temperature: 300 to 310°C Feed Temperature: 20 to 50°C

NOTE

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

