

Exelene® PP C0800

Polypropylene Impact Copolymer

Montachem International, Inc.

Message:

Applications:

Automobile battery cases

Auto parts, child car seats

Characteristics:

The Exelene resin PP C0800 meets the requirements of section 177.1520, paragraph C, from chapter 21 denominated "Olefin Polymers" from the Code of Federal Regulations of the FDA, to be utilized with direct food contact.

General Information			
Additive	Antioxidant		
Features	Antioxidant		
	Impact Copolymer		
Uses	Automotive Applications		
	Automotive Under the Hood		
	Child Safety Seats		
	Food Service Applications		
	Non-specific Food Applications		
Agency Ratings	FDA 21 CFR 177.1520(c)		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.898	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	65		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	24.1	MPa	ASTM D638
Tensile Elongation ² (Yield)	7.0	%	ASTM D638
Flexural Modulus - 1% Secant ³ (3.20 mm)	1310	MPa	ASTM D790B
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	110	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ⁴ (0.45 MPa, Unannealed)	90.0	°C	ASTM D648
NOTE			
1.	Type IV, 50 mm/min		
2.	Type IV, 50 mm/min		

3.	Method I (3 point load), 13 mm/min
4.	2°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

