GATONE[™] 5330FC

Polyetheretherketone

Solvay Specialities India Private Limited (SSIPL)

Message:

GATONE[™] 5330FC is a Polyetheretherketone (PEEK) material filled with 30% filler. It is available in Asia Pacific, Europe, or North America. Primary attribute of GATONE[™] 5330FC: Flame Rated.

Typical application of GATONE[™] 5330FC: Wire & Cable

General Information			
Filler / Reinforcement	Filler,30% Filler by Weight		
Agency Ratings	UL Unspecified Rating		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm³	ASTM D792
Water Absorption (24 hr)	0.080	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C, Injection Molded)	12000	MPa	ASTM D638
Tensile Strength (23°C, Injection Molded)	140	MPa	ASTM D638
Tensile Elongation (Break, 23°C, Injection Molded)	2.5	%	ASTM D638
Flexural Modulus (23°C, Injection Molded)	11100	MPa	ASTM D790
Flexural Strength (23°C, Injection Molded)	210	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection Molded)	50	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, Injection Molded)	315	°C	ASTM D648
Continuous Use Temperature	260	°C	ASTM D794
Glass Transition Temperature	148	°C	DSC
CLTE - Flow	2.1E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-0		UL 94
Oxygen Index	30	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

