

NYLOY® M-0030N-V N4

Polyamide 66

Nytex Composites Co., Ltd.

Message:

NYLOY® M-0030N-V N4 is a Polyamide 66 (Nylon 66) material. It is available in Asia Pacific or North America for injection molding.

Important attributes of NYLOY® M-0030N-V N4 are:

Flame Rated

Flame Retardant

Halogen Free

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Halogen Free		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.00	g/cm ³	ASTM D792
--	1.17	g/cm ³	ISO 1183
Molding Shrinkage			ASTM D955, ISO 294-4
Flow	1.4	%	
Across Flow	1.4	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785, ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
--	81.4	MPa	ASTM D638
--	80.0	MPa	ISO 527-2
Tensile Elongation			
Break	10	%	ASTM D638
Break	12	%	ISO 527-2
Flexural Modulus			
--	3430	MPa	ASTM D790
--	3200	MPa	ISO 178
Flexural Strength			
--	123	MPa	ASTM D790
--	119	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.5	kJ/m ²	ISO 179/1eA

Notched Izod Impact (23°C, 3.18 mm)	29	J/m	ASTM D256
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	250 to 265	°C	
Mold Temperature	70.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

