

MonoSol® M8630 - 2 mil

Polyvinyl Alcohol

MonoSol, LLC

Message:

MonoSol M8630 is a PVOH based thermoplastic film, soluble in cold water and manufactured using MonoSol's proprietary solution cast technology. MonoSol M8630 film has been specially formulated to be completely resistant to alkaline hydrolysis up to 14 pH. Coupling its rapid cold water solubility and compatibility to alkaline compounds, M8630 film is an excellent candidate for Detergent and Disinfectant unit dose packaging. It has good cold crack resistance and can be easily converted on all conventional packaging machines. Standard thicknesses are 25 micron (1.0 mil), 38 micron (1.5 mil), 51 micron (2.0 mil) and 76 micron (3.0 mil)..

General Information			
Features	Alkali Resistant		
	Biodegradable		
	Good Crack Resistance		
	Low Temperature Resistant		
	Water Soluble		
Uses	Film		
	Packaging		
Forms	Film		
Physical	Nominal Value	Unit	
Moisture Content (23°C) ¹	8.7	wt%	
Solubility ²			
Disintegration : 10°C, 50.8 µm	13.0	sec	
Dissolution : 10°C, 50.8 µm	23.0	sec	
Yield (50.8 µm)	15.6	m ² /kg	ASTM D4321
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	51	µm	
Film Thickness - Recommended / Available	25 µm, 38 µm, 51 µm and 76 µm		
Secant Modulus - 100%, MD	8.96	MPa	ASTM D882, ISO 527-3
Tensile Strength - MD			
Break	33.8	MPa	ASTM D882
--	33.8	MPa	ISO 527-3
Tensile Elongation - MD (Break)	530	%	ASTM D882, ISO 527-3
Dart Drop Impact	1300	g	ASTM D1709, DIN 53433
Elmendorf Tear Strength - MD			
--	1100	g	ASTM D1922
--	0.11	N	ISO 6383-2
NOTE			
1.	50%RH		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

