

KOPEL® KP3363HR

Thermoplastic Copolyester Elastomer

Kolon Plastics, Inc.

Message:

KOPEL® KP3363HR is a Thermoplastic Copolyester Elastomer (TPC-ET) product. It can be processed by extrusion and is available in Asia Pacific, Europe, Latin America, or North America. Primary characteristic: flame rated.

General Information			
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.3	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60% RH)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	63		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	36.3	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	540	%	ASTM D638
Flexural Modulus (23°C)	437	MPa	ASTM D790
Taber Abrasion Resistance (1000 Cycles, CS-17 Wheel)	7.00	mg	ASTM D1044
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C	120	J/m	
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	65.0	°C	ASTM D648A
Brittleness Temperature ¹	< -70.0	°C	ASTM D746
Peak Melting Temperature	210	°C	ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
NOTE			
1.	Solenoid Brittle Point		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT