

SUSTAMID 66 GLD 240

Polyamide 66
Röchling Sustaplast SE & Co. KG

Message:

Product characteristics
Excellent sliding properties
Low abrasion resistance
High mechanical strength
Typical fields of application
Mechanical engineering
Conveyor technology
Bottling industry

General Information	
Features	Good Abrasion Resistance
	High Strength
	Low Friction

Uses	Bottles
	Conveyors
	Engineered Applications

Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm ³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50% RH)	2.5	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	80		ISO 868
Ball Indentation Hardness	128	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2600	MPa	ISO 527-2
Tensile Stress (Yield)	65.0	MPa	ISO 527-2
Tensile Strain (Break)	10	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	3.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	60.0	°C	ISO 75-2/A
Continuous Use Temperature			
-- 1	-30.0 to 90.0	°C	
-- 2	< 150	°C	
Melting Temperature	260	°C	ISO 11357-3
CLTE - Flow	8.5E-5	cm/cm/°C	DIN 53752

Specific Heat	1700	J/kg/°C	DIN 52612
Thermal Conductivity	0.23	W/m/K	DIN 52612
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Electric Strength	25	kV/mm	IEC 60243-1
Dielectric Constant	3.50		IEC 60250
Dissipation Factor (50 Hz)	0.015		IEC 60250
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
3.00 mm	HB		
6.00 mm	HB		
NOTE			
1.	Long Term		
2.	Short Term		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

