

Tenac™ GA520

Acetal (POM) Homopolymer
Asahi Kasei Chemicals Corporation

Message:

Tenac™ GA520 is an Acetal (POM) Homopolymer product filled with glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, or North America. Applications of Tenac™ GA520 include engineering/industrial parts, automotive and housings.

Characteristics include:

- Flame Rated
- High Stiffness
- High Strength
- Homopolymer
- Medium Viscosity

General Information	
UL YellowCard	E48285-240813
Filler / Reinforcement	Glass Fiber
Features	High Stiffness
	High Strength
	Homopolymer
	Medium Viscosity
Uses	Engineering Parts
	Gears
	Housings

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.56	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	15	g/10 min	ISO 1133
Molding Shrinkage			Internal Method
Flow	1.5 to 1.8	%	
Across Flow	1.0 to 1.3	%	
Water Absorption (23°C, 24 hr, 50% RH)	0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	90		
R-Scale	120		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4300	MPa	ISO 527-2
Tensile Stress			
Yield	54.0	MPa	ISO 527-2
--	53.0	MPa	ASTM D638
Tensile Elongation			

Break	15	%	ASTM D638
Break	10	%	ISO 527-2
Flexural Modulus			
--	3930	MPa	ASTM D790
--	4100	MPa	ISO 178
Flexural Strength	100	MPa	ASTM D790
Taber Abrasion Resistance	23.0	mg	ASTM D1044
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.0	kJ/m ²	ISO 179
Notched Izod Impact	33	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	174	°C	ASTM D648
0.45 MPa, Unannealed	165	°C	ISO 75-2/B
1.8 MPa, Unannealed	152	°C	ASTM D648
1.8 MPa, Unannealed	118	°C	ISO 75-2/A
CLTE - Flow	7.0E-5	cm/cm/°C	ASTM D696, ISO 11359-2
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
0.710 mm	HB		
1.50 mm	HB		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

