

# Softell TKG 300N C11498

Polypropylene Copolymer  
LyondellBasell Industries

Message:

Softell TKG 300N C11498 is a 25% glass fiber reinforced PP copolymer, with high stiffness, excellent dimensional stability, excellent scratch resistance and low gloss. Product is available as a customized color matched, pellet form. This grade is delivered in C11498 color version.  
This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 25% filler by weight		
Features	Good dimensional stability		
	Rigidity, high		
	Copolymer		
	Gloss, low		
	Scratch resistance		
Uses	Application in Automobile Field		
	Car dashboard		
Appearance	Available colors		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.09	g/cm <sup>3</sup>	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus <sup>1</sup> (23°C)	2500	MPa	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	7.5	kJ/m <sup>2</sup>	ISO 179/1eA
23°C	35	kJ/m <sup>2</sup>	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	78.0	°C	ISO 75-2/A
NOTE			
1.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

