

Nylene® 5235 SP TF BK

Polyamide 6

Custom Resins Group

Message:

Nylene® 5235 SP TF BK is a Polyamide 6 (Nylon 6) material filled with 35% talc. It is available in North America.

General Information			
Filler / Reinforcement	Talc,35% Filler by Weight		
Appearance	Black		
Forms	Pellets		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	124	MPa	ASTM D638
Flexural Modulus (23°C)	6890	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	
Melting Temperature	216	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

