Bergamid™ BG6600-8059 RS HS BK001

Polyamide 66

PolyOne Corporation

Message:

Glass Beads Reinforced PA66 Compound with Heat Stabilized.

General Information			
Filler / Reinforcement	Glass beads, 30% filler by weight		
Appearance	Black		
Processing Method	Injection molding		
Physical	**Nominal Value**	**Unit**	**Test Method**
Specific Gravity	1.35	g/cm³	ASTM D792
Molding Shrinkage	0.90 - 1.2	%	ASTM D955
Mechanical	**Nominal Value**	**Unit**	**Test Method**
Tensile Strength [1]	80.0	MPa	ASTM D638
Flexural Modulus [2]	4500	MPa	ASTM D790
Flexural Strength [3]	130	MPa	ASTM D790
Impact	**Nominal Value**	**Unit**	**Test Method**
Notched Izod Impact (23°C, 3.20 mm)	35	J/m	ASTM D256
Thermal	**Nominal Value**	**Unit**	**Test Method**
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	80.0	°C	ASTM D648
Electrical	**Nominal Value**	**Unit**	**Test Method**
Surface Resistivity	1.0E+12	ohms	ASTM D257
Flammability	**Nominal Value**	**Unit**	**Test Method**
Flame Rating (1.60 mm)	HB		Internal method
Injection	**Nominal Value**	**Unit**	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	4.0 - 6.0	hr	
Rear Temperature	260 - 280	°C	
Middle Temperature	260 - 280	°C	
Front Temperature	260 - 280	°C	
Mold Temperature	65.0 - 85.0	°C	
Injection instructions			
Injection Pressure: MED-HIGHHold Pressure: MED-HIGHScrew Speed: MODERATEBack Pressure: LOW			
NOTE			
1.	5.0 mm/min		
2.	1.3 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China