

LEXAN™ FXE4472L resin

Polycarbonate

SABIC Innovative Plastics Asia Pacific

Message:

LEXAN FXE4472L is a 20% glass filled, impact modified polycarbonate with excellent light-shield capability. It is designed for high flow, superior surface appearance, enhance release and good impact ductility. FXE4472L is available in white color only and ideal for light-shield applications.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Additive	Impact Modifier		
Features	Good Impact Resistance		
	Good Mold Release		
	High Flow		
	Impact Modified		
	Outstanding Surface Finish		
Appearance	White		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	9.00	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal Method
Flow : 3.20 mm	0.20 to 0.30	%	
Across Flow : 3.20 mm	0.40 to 0.50	%	
Water Absorption			ISO 62
Saturation, 23°C	0.12	%	
Equilibrium, 23°C, 50% RH	0.040	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	6050	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield	38.0	MPa	
Break	44.0	MPa	
Tensile Elongation ³			ASTM D638
Yield	3.0	%	
Break	4.0	%	
Flexural Modulus ⁴ (50.0 mm Span)	5200	MPa	ASTM D790
Flexural Strength ⁵ (Yield, 50.0 mm Span)	82.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	170	J/m	ASTM D256

Unnotched Izod Impact (23°C)	920	J/m	ASTM D4812
Instrumented Dart Impact (23°C, Total Energy)	23.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.20 mm	129	°C	
1.8 MPa, Unannealed, 3.20 mm	123	°C	
Vicat Softening Temperature	134	°C	ISO 306/B120
RTI Elec	80.0	°C	UL 746
RTI Imp	80.0	°C	UL 746
RTI Str	80.0	°C	UL 746
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 to 4.0	hr	
Drying Time, Maximum	48	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 to 60	%	
Rear Temperature	266 to 288	°C	
Middle Temperature	277 to 299	°C	
Front Temperature	288 to 310	°C	
Nozzle Temperature	282 to 304	°C	
Processing (Melt) Temp	288 to 310	°C	
Mold Temperature	71.1 to 93.3	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	
Vent Depth	0.025 to 0.076	mm	
NOTE			
1.	5.0 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	1.3 mm/min		
5.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT