

WanBlend® WHT-885ET8

Thermoplastic Polyurethane Elastomer (Polyether)

Wanhua Chemical Group Co., Ltd.

Message:

WHT-885ET8 is polyether-based TPU compound available in cylinder form that can solve a wide range of static decay, static shielding and electromagnetic shielding problems.

Applications:

Electronic component packaging, Pipes, Belts, Component trays, etc.

General Information			
Features	Electromagnetic Shielding (EMI)		
Uses	Belts/Belt Repair		
	Electrical/Electronic Applications		
	Packaging		
	Piping		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	84		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	6.00	MPa	
300% Strain	11.0	MPa	
Tensile Strength	26.0	MPa	ASTM D412
Tensile Elongation (Break)	710	%	ASTM D412
Tear Strength	82.0	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-46.0	°C	ASTM D3417
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.0E+8	ohms	ASTM D257
Volume Resistivity	5.0E+8	ohms·cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	95.0 to 100	°C	
Drying Time	2.0 to 3.0	hr	
Rear Temperature	180	°C	
Middle Temperature	185	°C	
Front Temperature	190	°C	

Nozzle Temperature	190	°C
Injection Pressure	70.0	MPa
Extrusion	Nominal Value	Unit
Drying Temperature	95.0 to 100	°C
Drying Time	2.0 to 3.0	hr
Cylinder Zone 1 Temp.	180	°C
Cylinder Zone 3 Temp.	185	°C
Cylinder Zone 5 Temp.	190	°C
Die Temperature	185	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

