

TAIRIPRO T3002

Polypropylene Random Copolymer

Formosa Plastics Corporation

Message:

FCFC PP resin T3002 meets the requirements of FDA, RoHS and the certificates of environmental protection.

General Information			
Features	Random copolymer		
Agency Ratings	EC 1907/2006 (REACH)		
	FDA 21 CFR 177.1520		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.6	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.5 - 2.0	%	Internal method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	85		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	25.5	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	> 200	%	ASTM D638
Flexural Modulus (23°C)	834	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (23°C, 3.18 mm)	200	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 6.35 mm)	85.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Mold Temperature	30.0 - 50.0	°C	
Injection Pressure	3.92 - 8.83	MPa	
Injection instructions			
Screw Temp: 220 to 240°C			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

