

Amilan® CM3216G35UB1

Polyamide 66
Toray Resin Company

Message:

Amilan® CM3216G35UB1 is a Polyamide 66 (Nylon 66) product filled with 35% glass fiber. It is available in Asia Pacific, Europe, or North America. Characteristics include:
Flame Rated
Heat Resistant

General Information			
Filler / Reinforcement	Glass Fiber,35% Filler by Weight		
Features	Good Thermal Stability		
Part Marking Code	>PA66/PA610-GF35<		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.36	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 3.00 mm ¹	0.50 to 0.80	%	
Flow : 3.00 mm ²	0.20 to 0.40	%	
Water Absorption			
23°C, 24 hr	0.40	%	ASTM D570, ISO 62
Saturation, 23°C	3.0	%	ISO 62
Equilibrium, 23°C, 50% RH	1.1	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ISO 2039-2
M-Scale, 23°C	93		
R-Scale, 23°C	120		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
-40°C	280	MPa	
23°C	195	MPa	
80°C	120	MPa	
Tensile Strain			ISO 527-2
Break, -40°C	3.0	%	
Break, 23°C	3.0	%	
Break, 80°C	5.0	%	
Flexural Modulus			ISO 178
-40°C	11000	MPa	
23°C	9500	MPa	
80°C	4800	MPa	
Flexural Stress			ISO 178
-40°C	370	MPa	

23°C	290	MPa	
80°C	160	MPa	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-40°C	10	kJ/m ²	
23°C	14	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-40°C	89	kJ/m ²	
23°C	95	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	228	°C	ISO 75-2/B
1.8 MPa, Unannealed	225	°C	ISO 75-2/A
Melting Temperature	265	°C	DSC
CLTE - Flow	2.0E-5 to 3.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.42	W/m/K	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+5	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94
NOTE			
1.	80x80x3		
2.	80x80x3mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

