

SLOVAMID® 6 GF 30 HI

Polyamide 6

Plastcom

Message:

PA 6 for injection moulding, chemically strengthened with 30% glass fibre and with the content of thermoplastic kaoutchouc. Application: impacted mouldings and mouldings with high strength applied in automotive, electrical, engineering and consumergoods industry, eg.: grips for electro tools, hobby tools, gears, cases of the electrottools, cooling screws of blowers, electromotors, carrying parts in the automotive industry. With the increasing content of GF also the toughness, bending and tensile strength increase as well as the heat application increases up to 250°C and the shrinkage decreases. Delivered in natural mode and in the full RAL colour scale.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Impact Modifier		
Features	Chemically Coupled		
	High Strength		
	Impact Modified		
Uses	Automotive Applications		
	Consumer Applications		
	Electrical/Electronic Applications		
	Engineering Parts		
	Flexible Grips		
	Power/Other Tools		
Appearance	Colors Available		
	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PA 6		
Physical	Nominal Value	Unit	Test Method
Density	1.32	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0	g/10 min	ISO 1133
Molding Shrinkage			STM 64 0808
Across Flow	1.5	%	
Flow	1.2	%	
Water Content	0.15	%	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8800	MPa	ISO 527-2
Tensile Stress (Yield)	150	MPa	ISO 527-2
Tensile Strain (Yield)	3.5	%	ISO 527-2
Flexural Modulus	7950	MPa	ISO 178

Flexural Stress	220	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	12	kJ/m ²	
23°C	18	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-20°C	90	kJ/m ²	
23°C	90	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	195	°C	ISO 75-2/B
Vicat Softening Temperature	205	°C	ISO 306/B
Melting Temperature (DSC)	220	°C	ISO 3146
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Glow Wire Ignition Temperature	650	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	70.0 to 90.0	°C	
Injection Pressure	70.0 to 120	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT