# Epolene® N-14

### Low Density Polyethylene

#### Westlake Chemical Corporation

#### Message:

Epolene N-14 is a polyethylene (PE) homopolymer that can easily be melt blended with natural or synthetic waxes to increase the tensile strength of wax blends, improve the gloss of paper coatings, aid in pigment dispersion and mold release, and improve scuff and rub off resistance in printing inks. For these applications, six Epolene N-types, differing mainly in viscosity, are available to choose from (Epolene N-10, N-11, N-14, N-30, N-34, and N-35).

| General Information                      |  |       |             |
|--|--|-------|-------------|
| Features                                 | High Gloss   |       |             |
|  | Homopolymer  |       |             |
|  | Scratch Resistant  |       |             |
|  |  |       |             |
| Uses                                     | Adhesives  |       |             |
|  | Automotive Applications  |       |             |
|  | Blending   |       |             |
|  | Building Materials   |       |             |
|  | Coating Applications   |       |             |
|  | Construction Applications                                      |       |             |
|  | Packaging  |       |             |
|  |  |       |             |
| Forms                                    | Pellets  |       |             |
| Physical                                 | Nominal Value  |       |             |
| Molecular Weight <sup>1</sup>            | 4000   |       |             |
| Ring and Ball Softening Point            | 108  | °C    | ASTM E28    |
| Penetration Hardness <sup>2</sup> (25°C) | 300  | mm    | ASTM D5     |
| Fill Analysis                            | Nominal Value  | Unit  | Test Method |
| Melt Viscosity (125°C)                   | 150  | mPa·s |             |
| NOTE                                     |  |       |             |
|  | Molecular weight measured via Gel                              |       |             |
| 1.                                       | Permeation Chromatography<br>(GPC) using polystyrene standards |       |             |
|  | Needle under 100-g load for 5s,                                |       |             |
| 2.                                       | tenths of mm   |       |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

