

DOW™ Electrical & Telecommunications

DGDL-3479 NT

Colorable High Density Polyethylene Compound for Cable Jacketing

The Dow Chemical Company

Message:

Dow Electrical and Telecommunications DGDL-3479 NT is a High Density Polyethylene compound produced from resin made by the UNIPOL™ process technology. Dow Electrical and Telecommunications DGDL-3479 NT is a prime quality telephone and power cable natural jacketing that provides good toughness, excellent stress-cracking resistance, and abrasion resistance.

Specifications

Dow Electrical and Telecommunications DGDL-3479 NT meets the following raw material specifications:

ASTM D-1248: Type III, Class A, Category 5, Grades E10 and J4, J5

Cable jacketed with Dow Electrical and Telecommunications DGDL-3479 NT, using sound commercial extrusion practices, should meet the following specifications:

ICEA: S-61-402; NEMA WC5

ANSI: C8.35

IEC 60502

General Information			
Uses	Cable sheath		
	Cable sheath		
	Wire and cable applications		
Agency Ratings	ANSI C 8.35		
	ASTM D 1248, III, Class A, Cat. 5, Grade E10		
	ICEA S-61-402		
	IEC 60502		
	NEMA WC-5		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.942	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.040	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (10% Igepal, F0)	> 1000	hr	ASTM D1693
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	22.1	MPa	ASTM D638
Tensile Elongation (Break)	850	%	ASTM D638
Flexural Modulus	827	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature ¹	< -50.0	°C	ASTM D746
Electrical	Nominal Value	Test Method	
Dielectric Constant (1 MHz)	2.56	ASTM D1531	

Dissipation Factor (1 MHz)	3.0E-4		ASTM D1531
Additional Information	Nominal Value	Unit	Test Method
PENT	200	hr	ASTM F1473
Extrusion	Nominal Value	Unit	
Melt Temperature	235 - 255	°C	
Extrusion instructions			
加工和处理技巧:Dow AXELERON™ GP L-3479 NT 加工指导原则中包括使用建议的 455 到 491°F (235-255°C) 的熔体挤出温度范围.料筒在 180°F (82°C) 下干燥以去除湿气.但是,只有已知应用方式和加工设备的类型时,才能给出加工条件的具体建议.			
NOTE			

1.

F50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT