

Maxxam™ NR-218.S001-8080

Polypropylene
PolyOne Corporation

Message:
Mineral reinforced PP, good heat and UV stability

General Information			
Filler / Reinforcement	Mineral filler		
Appearance	Black		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Molding Shrinkage	0.90 - 1.1	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	26.5	MPa	ASTM D638
Tensile Elongation ² (Break)	40	%	ASTM D638
Flexural Modulus ³	2210	MPa	ASTM D790
Flexural Strength ⁴	39.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Injection Molded)	34	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	119	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 85.0	°C	
Drying Time	4.0 - 6.0	hr	
Processing (Melt) Temp	200 - 240	°C	
Mold Temperature	30.0 - 60.0	°C	
Injection instructions			
Injection Pressure: MED-HIGHHold Pressure: MED-HIGHScrew Speed: MODERATEBack Pressure: LOW			
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	1.3 mm/min		
4.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

