

Adell Polyamide BT-17

Polyamide 6

Adell Plastics, Inc.

Message:

Adell Polyamide BT-17 is a Polyamide 6 (Nylon 6) material filled with 33% glass fiber. It is available in North America.

Important attributes of Adell Polyamide BT-17 are:

Flame Rated

Impact Modified

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Additive	Impact Modifier		
Features	Impact Modified		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33 to 1.35	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
Water Absorption (24 hr)	0.70	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	87		
R-Scale	120		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	141	MPa	ASTM D638
Tensile Elongation (Break)	3.0 to 4.0	%	ASTM D638
Flexural Modulus	6550	MPa	ASTM D790
Flexural Strength	207	MPa	ASTM D790
Compressive Strength	172	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	140	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	218	°C	
1.8 MPa, Unannealed	213	°C	
Melting Temperature	210 to 221	°C	ASTM D789
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

