ECO-FLEX™ SA-75A

Thermoplastic Vulcanizate, Rubber Based SYNESIS LLC

Message:

ECO-FLEX™ SA-75A is a Thermoplastic Vulcanizate, Rubber Based (RTPV) product. It is available in North America. Applications of ECO-FLEX™ SA-75A include additive/masterbatch, automotive, consumer goods and sheet. Primary characteristic: eco-friendly/green.

General Information				
Recycled Content	Yes			
Uses	Automotive Applications			
	Blending			
	Consumer Applications			
	Sheet			
Forms	Pellets			
Physical	Nominal Value	Unit	Test Method	
Density	1.02	g/cm³	ISO 1183/A	
Hardness	Nominal Value	Unit	Test Method	
Shore Hardness (Shore A, 15 sec)	75		ISO 868	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Stress ¹ (100% Strain)	3.00	MPa	ISO 37	
Tensile Stress ² (Yield)	5.00	MPa	ISO 37	
Tensile Elongation ³ (Break)	400	%	ISO 37	
Tear Strength ⁴	26	kN/m	ISO 34-1	
Aging	Nominal Value	Unit	Test Method	
Change in Tensile Strength in Air (100°C, 1008 hr)	9.0	%	ISO 188	
Change in Tensile Strain at Break in Air (100°C, 1008 hr)	-11	%	ISO 188	
Change in Shore Hardness in Air (100°C, 1008 hr)	1.0		ISO 188	
Thermal	Nominal Value	Unit	Test Method	
Brittleness Temperature	-40.0	°C	ISO 812	
Flammability	Nominal Value	Unit	Test Method	
Burning Rate	39	mm/min	SAE J369	
Additional Information	Nominal Value		Test Method	
Ozone Resistance ⁵	Pass - No Cracking		ISO 1431-1	
NOTE				
1.	Type 1, 50 mm/min			
2.	Type 1, 50 mm/min			
3.	Type 1, 50 mm/min			

4.	Method Bb, Angle (Nicked), 50 mm/min
5.	Procedure A, 20% Elongation, 51 MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

