

CERTENE™ LLBF-118B

Linear Low Density Polyethylene
Muehlstein

Message:

LLBF-118B is a certified prime resin with Butene-comonomer, designed for production of Blown films used in general purpose packaging. LLBF-118B features excellent combination of easy processability with good film strength as well as wide heat sealing temperature range. LLBF-118B applications include garment bags, produce bags and liners. LLBF-118B contains NO slip and Medium antiblock. LLBF-118B complies with FDA regulation 21CFR 177.1520(c)3.2a, conditions of use A-H per 21CFR 176.170(c), Table 2.

General Information			
Additive	Moderate caking resistance		
Features	Butene comonomer		
	Workability, good		
	Heat sealable		
	Good strength		
	Compliance of Food Exposure		
Uses	Moderate caking resistance		
	Packaging		
	Films		
	Lining		
	Bags		
Agency Ratings	Food packaging		
	FDA 21 CFR 176.170(c), Table 2 Conditions of use A- H		
Forms	FDA 21 CFR 177.1520(c) 3.2a		
	Particle		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.918	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	µm	ASTM D882
secant modulus			
1% secant, MD: 25 µm	193	MPa	ASTM D882
1% secant, TD: 25 µm	223	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield, 25 µm	9.38	MPa	ASTM D882
TD: Yield, 25 µm	9.51	MPa	ASTM D882

MD: Break, 25 µm	34.5	MPa	ASTM D882
TD: Break, 25 µm	27.6	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Break, 25 µm	550	%	ASTM D882
TD: Break, 25 µm	820	%	ASTM D882
Dart Drop Impact ¹ (25 µm)	80	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 25 µm	100	g	ASTM D1922
TD : 25 µm	550	g	ASTM D1922
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 25.4 µm, Blown Film)	35		ASTM D2457
Haze (25.4 µm, Blown Film)	20	%	ASTM D1003
Additional Information			
Film Specimen: 1.0 mil (25 µm) film, melt temperature 390-395°F, blow-up-ratio 2.5 :1.			
NOTE			
1.	F50		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

