

# APEX® 69-8004-J

Flexible Polyvinyl Chloride

Teknor Apex Company

Message:

APEX® 69-8004-J is a flexible polyvinyl chloride material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is: extrusion.

APEX® The main features of 69-8004-J are:

ROHS certification

Good flexibility

Typical application areas include:

Wire and cable

military applications

Hose

General Information			
Features	Flexibility at low temperatures		
	Antibacterial property		
Uses	Pipe fittings		
	Military cable insulation material		
Agency Ratings	MIL I-631-D Class I, Type I		
RoHS Compliance	RoHS compliance		
Appearance	Clear/transparent		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	70		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	13.1	MPa	ASTM D638
Tensile Elongation (Break)	400	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-65.0	°C	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+11	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	22	%	ASTM D2863
Additional Information			
温度额定值:60 °C最大伸长保持率,UL 1581,烘箱老化,7天,100°C:85 % 拉伸强度保持率,UL 1581,烘箱老化,7天,100°C: 109 %			
Extrusion	Nominal Value	Unit	
Melt Temperature	174	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

