

CompaDur® 121 GK 30 natural (009)

Polybutylene Terephthalate

DimeLika Plast GmbH

Message:

PBT, injection molding grade, 30% glass beads, heat stabilized, low warp, good surface.

General Information			
Filler / Reinforcement	Glass beads, 30% filler by weight		
Additive	heat stabilizer		
Features	Low warpage		
	Thermal Stability		
	Excellent appearance		
Appearance	Natural color		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.54	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	14.0	cm³/10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4200	MPa	ISO 527-2/1
Tensile Stress (Break)	50.0	MPa	ISO 527-2/5
Tensile Strain (Break)	3.0	%	ISO 527-2/5
Flammability	Nominal Value	Test Method	
Flame Rating (0.800 mm)	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	120 - 140	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	250 - 265	°C	
Middle Temperature	250 - 265	°C	
Front Temperature	250 - 265	°C	
Nozzle Temperature	260 - 270	°C	
Processing (Melt) Temp	260 - 270	°C	
Mold Temperature	75.0 - 100	°C	
Injection Pressure	60.0 - 100	MPa	
Injection Rate	Fast		
Holding Pressure	1.00 - 3.00	MPa	
Back Pressure	40.0 - 80.0	MPa	
Screw Speed	80	rpm	

Injection instructions

Melt residence time: 5 to 10 mins
Nozzle: open

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

