

Next ABS SX-02AVBK

Acrylonitrile Butadiene Styrene

Next Polymers Ltd.

Message:

Description

ABS Un Filled Black Compound

Product Applications

Typical application such as computer monitor,Printer,Photocopying machine,calculators ,Batttries,Lighting diffusers, Auto exterior parts etc

Benefits

Good low Temperature Toughness, High gloss & weather resistance

General Information			
Features	Good Weather Resistance		
	High Gloss		
	Low Temperature Resistant		
Uses	Automotive Exterior Parts		
	Batteries		
	Calculators		
	Computer Components		
	Printer		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/5.0 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	0.60	%	
Across Flow	0.60	%	
Water Absorption			ASTM D570
23°C, 24 hr	0.30	%	
Saturation ¹	0.70	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	95		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2000	MPa	ASTM D638
Tensile Strength	40.0	MPa	ASTM D638
Tensile Elongation (Break)	17	%	ASTM D638
Flexural Modulus	2100	MPa	ASTM D790

Flexural Strength	72.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	160	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	110	°C	
1.8 MPa, Unannealed	95.0	°C	
Vicat Softening Temperature	105	°C	ASTM D1525
RTI Elec	60.0	°C	UL 746
RTI Imp	60.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	18	kV/mm	ASTM D149
Arc Resistance	160	sec	ASTM D495
Arc Resistance	PLC 5		ASTM D495
Comparative Tracking Index (CTI)	> 550	V	UL 746
Comparative Tracking Index (CTI)	PLC 0		UL 746
Hot-wire Ignition (HWI)	22	sec	UL 746
Hot-wire Ignition (HWI)	PLC 3		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature - Hot Air Dryer	70.0	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	210 to 220	°C	
Middle Temperature	220 to 230	°C	
Front Temperature	230 to 240	°C	
Mold Temperature	45.0 to 65.0	°C	
NOTE			
1.	Immersed		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT