

# MAJORIS DT301 - 8229

Polypropylene

AD majoris

## Message:

DT301 - 8229 is a 30% mineral filled polypropylene compound intended for injection moulding.

The product is available in both black (DT301- 8229) and natural (DT301) but other colours can be provided on request.

DT301 - 8229 has a medium flow rate, very good processability and excellent mechanical properties.

DT301 - 8229 has been developed especially for the automotive under the bonnet application requiring excellent long- term heat stability and electrical industry.

## APPLICATIONS

Fuse and connector boxes

Miscellaneous electrical components

Household appliances

Automotive climate control parts

Air conditioning parts

Heater housings

Products requiring high rigidity, high dimensional stability, low shrinkage and good long term heat resistance, high heat distortion temperature can suitably be made from DT301 - 8229.

General Information	
Filler / Reinforcement	Mineral filler, 30% filler by weight
Additive	heat stabilizer
Features	Good dimensional stability
	Rigidity, high
	Recyclable materials
	Workability, good
	Medium liquidity
	Heat resistance, high
	Thermal Stability
	Thermal stability, good
Uses	Low shrinkage
	Electrical components
	Electrical appliances
	Parts under the hood of a car
	Application in Automobile Field
Appearance	Shell
	Black
	Available colors
Forms	Natural color
	Particle
Processing Method	Injection molding

Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0	g/10 min	ISO 1133
Molding Shrinkage	0.70 - 1.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	37.0	MPa	ISO 527-2/5
Tensile Strain (Yield)	8.0	%	ISO 527-2/5
Flexural Modulus <sup>1</sup>	3200	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C	1.5	kJ/m <sup>2</sup>	ISO 179/1eA
23°C	3.0	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	40	kJ/m <sup>2</sup>	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	129	°C	ISO 75-2/B
1.8 MPa, not annealed	75.0	°C	ISO 75-2/A
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Atomization-100°C/16H	3.4E-4	g	DIN 75201
Emission	25.0	µgC/g	VDA 277
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	210 - 260	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Moderate		
Injection instructions			
Holding pressure: 50 to 70% of the injection pressure			
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT