

Osterlene® HD-.35-953

High Density Polyethylene

Osterman & Company

Message:

HD-.35-953 is a high density polyethylene with applications for use in HIC bottles, toys and windshield wash bottles.

General Information			
Features	High density		
Uses	Bottle		
	Toys		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	0.954	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.37	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (F50)	25.0	hr	ASTM D1693
Additional Information			
ESCR F50, ASTM D2561: >500 hr			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

