Hostacom TSOP EM5 2639

Polypropylene Copolymer LyondellBasell Industries

Message:

Hostacom TSOP EM5 2639 is a high melt flow, UV stabilised, mineral filled polypropylene copolymer which exhibits high impact combined with excellent stiffness. The grade has been designed for large automotive applications such as instrument panels and interior trim.

General Information			
Filler / Reinforcement	Mineral		
Additive	UV Stabilizer		
Features	Copolymer		
	Good Processability		
	Good UV Resistance		
	High Flow		
	High Impact Resistance		
	High Stiffness		
Uses	Automotive Applications		
	Automotive Instrument Panel		
	Automotive Interior Parts		
	Automotive Interior Trim		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	28	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	> 76		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	19.0	МРа	ISO 527-2/50
Tensile Strain (Break, 23°C)	> 80	%	ISO 527-2/50
Flexural Modulus ¹ (23°C)	1750	МРа	ISO 178
Flexural Stress (23°C)	31.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	> 2.0	kJ/m²	
23°C	> 20	kJ/m²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa,		°C	ICO 7F 2/A
Unannealed)	57.0	°C	ISO 75-2/A

NOTE

1. 2.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2