

4DUR® 9K23100 HI

Polybutylene Terephthalate

4Plas

Message:

4DUR 9K23100 HI is a Standard Flow FR-V0 Heat Stabilised, Impact Modified PBT

General Information			
Additive	Impact modifier		
	heat stabilizer		
Features	Impact modification		
	Thermal Stability		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	ISO 1183
Molding Shrinkage			
Vertical flow direction	1.6	%	
Flow direction	1.6	%	
Water Absorption ¹ (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Moisture Content	< 800	ppm	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2500	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	45.0	MPa	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	6.0	kJ/m ²	ISO 180/1A
23°C	8.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	130	°C	ISO 75-2/B
1.8 MPa, not annealed	60.0	°C	ISO 75-2/A
Vicat Softening Temperature	75.0	°C	ISO 306/B
Melting Temperature ²	225	°C	ISO 11357
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94

0.750 mm	V-2	UL 94
1.60 mm	V-0	UL 94
Glow Wire Flammability Index (2.00 mm)	960	°C IEC 60695-2-12
Glow Wire Ignition Temperature (2.00 mm)	675	°C IEC 60695-2-13
Injection	Nominal Value	Unit
Drying Temperature	120	°C
Drying Time	2.0 - 4.0	hr
Suggested Max Moisture	0.040	%
Processing (Melt) Temp	240 - 260	°C
Mold Temperature	60.0 - 100	°C
Injection Rate	Moderate-Fast	
Holding Pressure	40.0 - 80.0	MPa
Screw Speed	300	rpm
Injection instructions		
Feed Throat Temperature: 50 - 70 °C Back Pressure: Low		
NOTE		
1.	24 Hrs	
2.	10 K/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

