

# RTP 4402

Polyamide

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'  
The data for this material has not been recently verified.  
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Features	High Temperature Strength		
RoHS Compliance	Contact Manufacturer		
Appearance	Black		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.29	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow			ASTM D955
3.18 mm, Injection Molded	0.40 to 0.50	%	
6.35 mm, Injection Molded	0.47	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (Injection Molded)	5860	MPa	ASTM D638
Tensile Strength	96.0	MPa	ASTM D638
Tensile Elongation (Yield, Injection Molded)	1.7	%	ASTM D638
Flexural Modulus (Injection Molded)	5860	MPa	ASTM D790
Flexural Strength (Injection Molded)	138	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm, Injection Molded)	48	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	320	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, Injection Molded)	152	°C	ASTM D648
Injection	Nominal Value	Unit	
Rear Temperature	304 to 332	°C	
Middle Temperature	304 to 332	°C	
Front Temperature	304 to 332	°C	
Mold Temperature	135 to 160	°C	
Injection Pressure	69.0 to 103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

