

Ducor® 1101 S

Polypropylene Homopolymer

Ducor Petrochemicals BV

Message:

Ducor 1101 S is a polypropylene homopolymer fibre grade characterized by high flowability, medium molecular weight distribution and medium crystallinity providing excellent and consistent process and product behaviour. Ducor 1101 S is particularly suitable for the production of continuous filaments (CF) and high resilience bulked continuous filaments (BCF). The product comprises an advanced phenol free stabiliser package providing superior gasfading resistance and inherent basic UV stability.

Food Contact Applications: This grade is in compliance with most regulations regarding food contact applications (EU, FDA). Specific information is available upon request.

General Information			
Additive	Anti-gas fading 2		
	UV Stabilizer		
Features	Food Contact Acceptable		
	Gas-fading Resistant		
	Good Processability		
	Good UV Resistance		
	High Flow		
	Homopolymer		
	Med.-Wide Molecular Weight Distrib.		
	Semi Crystalline		
Uses	BCF Yarn		
	Fibers		
	Filaments		
Agency Ratings	EC 1907/2006 (REACH)		
	EC 1935/2004		
	EN 71-3		
	EU 10/2011		
	EU 2000/53/EC		
	EU 2002/96/EC (WEEE)		
	EU 2005/84/EC		
	EU 94/62/EC		
	FDA 21 CFR 177.1520(a) 1 (i)		
	FDA 21 CFR 177.1520(c) 1.1a		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ISO 1183

Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	25	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	78.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1500	MPa	ISO 527-2/1
Tensile Stress (Yield)	35.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	8.0	%	
Break	> 50	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	1.5	kJ/m ²	
23°C	2.5	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	13	kJ/m ²	
23°C	110	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	85.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	55.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	154	°C	ISO 306/A
--	90.0	°C	ISO 306/B
Melting Temperature (DSC)	163	°C	ISO 3146

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT