## Vaycron® XA78399

## Thermoplastic Elastomer INEOS Compounds

## Message:

Description: Vinyl based Thermoplastic Elastomer

Colour: Black and Natural

Applications: Conservatory Glazing Gasket Specification: Complies with BS7412 Category A

General Information			
Uses	Gaskets		
Agency Ratings	BS 7412:2002 Class A		
Appearance	Black		
	Natural Color		
Forms	Pellets		
Processing Method	Extrusion		
Physical Physical	Nominal Value	Unit	Test Method
Density <sup>1</sup>	1.35	g/cm³	BS 2782
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 15 sec, 23°C)	65		BS 2782
BS Softness	61	%	BS 2782
Cold Flexibility	-23	°C	BS 2782
Resilience - Polycarbonate	Pass (at 1.1% strain)		BS EN 4599:1997
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength <sup>2</sup>	11.5	MPa	BS 2782
Tensile Elongation <sup>3</sup> (Break)	330	%	BS 2782
Compression Set (70°C, 22 hr)	60	%	BS 2782
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	160	°C	
Cylinder Zone 2 Temp.	160	°C	
Cylinder Zone 3 Temp.	160	°C	
Cylinder Zone 4 Temp.	160	°C	
NOTE			
1.	Natural, varies with colour		
2.	500 mm/min		
3.	500 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

